

ART. **LORD** CAT. **EXTRA** LEATHER

Chrome tanned bull hides with European origin - Pigmented - Full grain - Through-dyeing aniline
Thickness 1.3 - 1.5 mm

PROPERTY	TEST METHOD	PERFORMANCE
COLOR FASTNESS		
Dry rub fastness - 1.000 cycles:	UNI EN ISO 11640	≥4 Grey Scale
Wet rub fastness - 250 cycles:	UNI EN ISO 11640	≥4 Grey Scale
Alkaline perspiration rub fastness - 80 cycles:	UNI EN ISO 11640	≥4 Grey Scale
Light fastness:	UNI EN ISO 105-B02	≥6 Blue Scale

PHYSICAL CHARACTERISTICS

Adhesion of finishing:	UNI EN ISO 11644	≥ 2 N/10mm
Tear resistance:	UNI EN ISO 3377-1	≥ 20 N
Flex resistance - 50.000 cycles:	UNI EN ISO 5402	No cracks

FLAMMABILITY

Cigarette test – Match test:	UNI EN 1021-1/UNI EN 1021-2	Complies
Cigarette Ignition Resistance:	NFPA 260/UFAC	Complies
FS191 Method 5903-Port Authority of New York & New Jersey:		On demand
IMO Resolution A.652 (16):		Complies
California TB 117 Section E:		Complies

Our leather is processed in conformity with REACH regulation

CLEANING AND MAINTENANCE

- | | |
|--|--|
|  Avoid placing leather in direct sun cloth and mild soap |  Spots can be cleaned with a lightly damp |
|  Keep the leather away from direct heat |  Dry immediately after treatment |
|  Dust regularly with a soft and dry cloth |  Do not rub. Use a light circular motion working toward the center of the stain |

CERTIFICATIONS



UNI 11239



ISO 14025



ISO 14067/C02



RAL-UZ 148



RAL-GZ 430