



Date of Issue: 10/10/2025
 Report Number: 25-002966
 Revision Number: 1
 Date Order Received: 10/08/2025

For the Account of: Kvadrat A/S
 Lundbergsvej 10
 8400 Ebeltoft

Client's Identification: HALLINGDAL 65
 Alta DWR Drapery

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	35.8	31.7	11	0.0	0.0
2	36.0	27.9	23	0.0	6.0
3	36.1	28.5	21	0.0	6.0
4	36.2	32.5	10	0.0	0.0
5	35.4	32.1	9	0.0	0.0
6	36.1	31.2	14	0.0	0.0
7	35.5	32.1	10	0.0	0.0
8	36.1	32.9	9	0.0	3.0
9	35.7	32.3	10	0.0	0.0
10	35.5	28.7	19	0.0	5.0
Average	35.8	31.0	14	0.0	2.0

NOTES

Approximate weight (oz./sq. yd): 17.6

Standard Deviation: 5.4

Mean + 3 SD: 30.2

Product Configuration: Single Layer Multi Layer
 Material Tested: Initially
 Test Environment: 70 ±4°F, 50 ±5% Relative Humidity
 Conditioning: Oven at 220°F (30 minutes) 70 ±4°F & 65 ±5%RH for 24 hours
 Sampling: As Received
 Intended End-use: Drapery

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceed mean + 3 SD

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply
- Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 10/09/2025