

Our Ref: SW/SW

28 April 2025

Report 429052 Rev. 1**Page: 1 of 2**

Wooltex UK Limited
Woodland Mill
Dale Street
Longwood
Huddersfield, Yorkshire
HD3 4TG

Contact: Laura Wood

DATE RECEIVED : 22 NOV 2024
QUALITY/REFERENCE : TECHNICOLOUR 150
REPUTED FIBRE CONTENT : 100% WOOL
FABRIC DESCRIPTION : WOVEN
PERFORMANCE STANDARD : BS2543:2004 & BS EN 14465:2003 + A1:2006
TEST PERFORMANCE DATE(S) : 22/11/2024 - 28/04/2025

**REPORT SUMMARY**

Tests	Method	Pass	Fail	Requirement
Seam slippage	BS EN ISO 13936-2:2004			No requirement
Resistance to pilling	BS EN ISO 12945-2:2000			No requirement



S. WISEMAN
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of Eurofins MTS Consumer Product Testing Services Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

This report replaces report number 429052 dated 22/11/24. customer requested pilling & seam slippage on seperate report

28 April 2025

Page: 2 of 2**Report 429052 Rev. 1****PHYSICAL****BS EN ISO 13936-2:2004 Seam Slippage**

	Length	Width
Seam opening at 180 N	10.0 mm	8.1 mm

Requirement:
No requirement

BS EN ISO 12945-2:2000 Determination of fabric propensity to Surface Fuzzing & Pilling (Modified Martindale)

Revs	Grade
500	4
1000	3-4
2000	3-4
5000	4

Requirement:
No requirement

Sample tested: As received

Tested using standard worsted abradant as per BS EN ISO 12947-1